

DRY GROUND MICA POWDERS - CALCINED

Calcined dry ground mica powders are particularly useful as fillers and extenders for welding rods.



CHEMICAL PROPERTIES

SiO ₂	Al ₂ O ₃	K ₂ O	Na ₂ O	MgO	CaO	TiO ₂	Fe ₂ O ₃	PH
47 - 50%	28 ~ 3%	8 ~ 11%	0.6 ~ 0.9%	0.5 ~ 0.8%	0.3 ~ 0.6%	0.6 ~ 0.9%	8% max	7.8

PHYSICAL PROPERTIES

Colour	Melting Point	Purity
Golden	1250°C	> 99.5%

PRODUCT SPECIFICATIONS

PRODUCT	Particle Distribution (%)				Bulk density (g/ml)
	+400 µm	+160 µm	+100 µm	+45 µm	
Mica C60	< 0.2	10 - 20	45 - 65	< 85	0.3 / 0.4